

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (currently amended) A method for preparing a flexible magnetic insole for providing magnetotherapy to a foot, the steps comprising:

providing a laminated sheet, said laminated sheet having a leather upper, a flexible magnetic core coupled to said leather upper, and a cushioning base coupled to said flexible magnetic core;

said flexible magnetic core including permanent magnetic particles embedded therein with said magnetic particles forming at least one magnetic zone of a first polarity and a plurality of magnetic zones of a second polarity;

said at least one magnetic zone of first polarity and said plurality of magnetic zones of second polarity being positioned contiguous with one another;

said at least one magnetic zone of first polarity being contiguous with three of said zones of second polarity, said at least one magnetic zone of first polarity being regular in shape;

cutting an insole section from said laminated sheet; and

perforating said insole section to provide ventilation holes through said insole section.

2. (original) The method for preparing a flexible magnetic insole for providing magnetotherapy to a foot as set forth in Claim 1, wherein the step of perforating an insole section further comprises:

4                                perforating said laminated sheet prior to cutting said insole section to  
provide a perforated insole section.

3.     (original)     The method for preparing a flexible magnetic insole for providing  
2           magnetotherapy to a foot as set forth in Claim 1, wherein the step of providing a  
laminated sheet further comprises:

4                                providing a leather sheet, said leather sheet forming said leather upper;  
providing a flexible magnetic sheet, said flexible magnetic sheet forming  
6           said flexible magnetic core;  
coupling said flexible magnetic sheet to said leather sheet;  
8                                providing a sheet of cushioning material, said sheet of cushioning  
material forming said cushioning base; and  
10                                coupling said sheet of cushioning material to said flexible magnetic  
sheet; whereby  
12                                a three-layer laminated sheet is provided from which flexible magnetic  
insoles may be cut.

4.     (original)     The method for preparing a flexible magnetic insole for providing  
2           magnetotherapy to a foot as set forth in Claim 3, wherein the step of providing a  
flexible magnetic sheet further comprises:

4                                mixing strongly magnetizable material with an elastic binder to form a  
mixture;  
6                                rolling said mixture into a sheet; and

magnetizing said sheet; whereby

8                   said flexible magnetic sheet is produced in a controllable fashion from a  
  
strongly magnetizable material and an elastic binder.

5.     (original)     The method for preparing a flexible magnetic insole for providing  
2                   magnetotherapy to a foot as set forth in Claim 4, wherein said strongly magnetizable  
  
material further comprises:

4                   powdered or particulate strontium ferrite.

6.     (original)     The method for preparing a flexible magnetic insole for providing  
2                   magnetotherapy to a foot as set forth in Claim 4, wherein said elastic binder further  
  
comprises:

4                   an elastomer selected from the group comprising neoprene, styrene-  
  
butadiene rubber (SBR), and acrylonitrile-butadiene rubber (NBR or nitrile).

7.     (original)     The method for preparing a flexible magnetic insole for providing  
2                   magnetotherapy to a foot as set forth in Claim 4, wherein said step of mixing strongly  
  
magnetizable material with an elastic binder further comprises:

4                   mixing strongly magnetizable material with an elastic binder, stearic  
  
acid, and a mold-release agent.

8.     (original)     The method for preparing a flexible magnetic insole for providing  
2                   magnetotherapy to a foot as set forth in Claim 7, wherein said step of mixing strongly

magnetizable material with an elastic binder further comprises:

4                    mixing zinc oxide with said strongly magnetizable material, elastic  
binder, stearic acid, and mold-release agent, said zinc oxide providing cross  
6                    linking of said elastic binder.

9.        (original)        The method for preparing a flexible magnetic insole for providing  
2                    magnetotherapy to a foot as set forth in Claim 4, wherein said step of rolling said  
mixture into a sheet further comprises:

4                    rolling and pressing said mixture at an elevated temperature to cure said  
mixture and to provide a magnetizable sheet.

10.       (original)        The method of preparing a flexible magnetic insole for providing  
2                    magnetotherapy to a foot as set forth in Claim 9, wherein said step of rolling and  
pressing said mixture further comprises:

4                    providing a nylon mesh; and  
rolling and pressing said nylon mesh with said mixture; whereby  
6                    said nylon mesh is incorporated into said magnetizable sheet and  
provides mechanical support and greater strength to said magnetizable sheet.

11.       (original)        The method for preparing a flexible magnetic insole for providing  
2                    magnetotherapy to a foot as set forth in Claim 4, wherein said step of magnetizing said  
sheet further comprises:

4                    providing a magnetizing press having first and second jaws, said first jaw

incorporating permanent magnets having a first polarity configuration, said  
6 second jaw incorporating permanent magnets having a second polarity  
configuration, said second polarity configuration being the opposite polarity of  
8 said first polarity configuration so that said permanent magnets of said first jaw  
meet permanent magnets of opposite polarity in said second jaw;

10 providing a dielectric envelope for fitting between said first and second  
jaws;

12 placing at least a portion of said sheet into said dielectric envelope;

placing said dielectric envelope between said first and second jaws;

14 pressing said dielectric envelope and said sheet between said first and  
second jaws; and

16 removing said sheet from between said first and second jaws; whereby

said sheet is magnetized by said magnetizing press, said sheet more  
18 easily removable from said magnetizing press by said dielectric envelope as said  
dielectric envelope is not attracted to said magnetizing press and as said  
20 dielectric envelope provides mechanical support for said sheet and prevents  
tearing or ripping of said sheet when removed from said magnetizing press.

12. (original) The method for preparing a flexible magnetic insole for providing  
2 magnetotherapy to a foot as set forth in Claim 11, wherein said dielectric envelope  
comprises a brass envelope.

13. (original) The method for preparing a flexible magnetic insole for providing

2 magnetotherapy to a foot as set forth in Claim 11, wherein said step of pressing said  
dielectric envelope and said sheet between said first and second jaws further comprises:

4 heating said sheet above a Curie temperature of said sheet to better  
magnetize said sheet; and

6 cooling said sheet below said Curie temperature to fix said magnetism in  
said sheet.

14. (original) The method for preparing a flexible magnetic insole for providing  
2 magnetotherapy to a foot as set forth in Claim 11, wherein said step of pressing said  
dielectric envelope and said sheet between said first and second jaws further comprises:

4 pressing said dielectric and said sheet at an elevated pressure.

15. (currently amended) A method for preparing a flexible magnetic insole for providing  
2 magnetotherapy to a foot, the steps comprising:

providing a leather sheet, said leather sheet forming a leather upper;

4 mixing strongly magnetizable strontium ferrite material with an elastic  
neoprene binder, stearic acid, a mold-release agent, and zinc oxide to form a  
6 magnetizable mixture;

providing nylon mesh;

8 rolling and pressing said magnetizable mixture with said nylon mesh,  
said rolling and pressing occurring at an elevated temperature to cure said  
10 magnetizable mixture, said nylon mesh providing mechanical support and  
greater strength to said magnetizable sheet;

12                    providing a magnetizing press having first and second jaws, said first jaw  
incorporating strongly magnetic permanent magnets having a first polarity  
14                    configuration, said second jaw incorporating strongly magnetic permanent  
magnets having a second polarity configuration, said second polarity  
16                    configuration being the opposite polarity of said first polarity configuration so  
that said permanent magnets of said first jaw are oppositely opposed said  
18                    permanent magnets of opposite polarity of said second jaw when said  
magnetizing press is closed;

20                    providing a dielectric brass envelope for fitting between said first and  
second jaws;

22                    placing at least a portion of said magnetizable sheet into said dielectric  
brass envelope, said magnetizable sheet more easily removable from said  
24                    magnetizing press by said dielectric brass envelope as said dielectric brass  
envelope is not attracted to said magnetizing press and as said dielectric  
26                    envelope provides mechanical support for said magnetizable sheet and prevents  
tearing or ripping of said magnetizable sheet when removed from said  
28                    magnetizing press;

                     placing said dielectric brass envelope between said first and second jaws;  
30                    closing said magnetizing press;

                     pressing said dielectric envelope and said magnetizable sheet between  
32                    said first and second jaws at an elevated pressure, said magnetizable sheet  
magnetized during said pressing to provide a flexible magnetic sheet;

34                    heating said magnetizable sheet above a Curie temperature of said

magnetizable sheet to better magnetize said sheet;

36                    said magnetizable sheet including permanent magnetic particles  
embedded therein with said magnetic particles forming at least one magnetic  
38                    zone of a first polarity and a plurality of magnetic zones of a second polarity;  
said at least one magnetic zone of first polarity and said plurality of  
40                    magnetic zones of second polarity being positioned contiguous with one another;  
said at least one magnetic zone of first polarity being contiguous with  
42                    three of said zones of second polarity, said at least one magnetic zone of first  
polarity being regular in shape;

44                    cooling said flexible magnetic sheet below said Curie temperature to fix  
said magnetism in said flexible magnetic sheet;

46                    removing said flexible magnetic sheet from said magnetizing press;  
coupling said flexible magnetic sheet to said leather sheet;

48                    providing a sheet of cushioning material, said sheet of cushioning  
material forming a cushioning base;

50                    coupling said sheet of cushioning material to said flexible magnetic sheet  
to provide a three-layer laminated sheet from which flexible magnetic insoles  
52                    may be cut;

cutting an insole section from said laminated sheet; and  
54                    providing ventilation holes through said insole section.

16. (original) The method for preparing a flexible magnetic insole of Claim 15,  
2                    wherein said first and second polarity configurations of said first and second jaws is



selected from the group consisting of:

alternating magnetic triangles, alternating magnetic squares, and series of  
alternating concentric circles; whereby

said magnetizable sheet is magnetized with a magnetic polarity  
configuration the same as said first and second jaws.

17. (original) A method for preparing a flexible magnetic insole for providing  
magnetotherapy to a foot, the steps comprising:

providing a laminated sheet, said laminated sheet having a leather upper,  
a flexible magnetic core coupled to said leather upper, and a cushioning base  
coupled to said flexible magnetic core;

said flexible magnetic core including permanent magnetic particles  
embedded therein with said magnetic particles forming at least one magnetic  
zone of a first polarity and a plurality of magnetic zones of a second polarity;

said at least one magnetic zone of first polarity and said plurality of  
magnetic zones of second polarity being positioned contiguous with one another;

said at least one magnetic zone of first polarity being contiguous with  
three of said zones of second polarity, said at least one magnetic zone of first  
polarity being triangular in shape;

cutting an insole section from said laminated sheet; and

perforating said insole section to provide ventilation holes through said  
insole section.

18. (original) A method for preparing a flexible magnetic insole for providing  
magnetotherapy to a foot, the steps comprising:

providing a leather sheet, said leather sheet forming a leather upper;

mixing strongly magnetizable strontium ferrite material with an elastic  
neoprene binder, stearic acid, a mold-release agent, and zinc oxide to form a  
magnetizable mixture;

providing nylon mesh;

rolling and pressing said magnetizable mixture with said nylon mesh,  
said rolling and pressing occurring at an elevated temperature to cure said  
magnetizable mixture, said nylon mesh providing mechanical support and  
greater strength to said magnetizable sheet;

providing a magnetizing press having first and second jaws, said first jaw  
incorporating strongly magnetic permanent magnets having a first polarity  
configuration, said second jaw incorporating strongly magnetic permanent  
magnets having a second polarity configuration, said second polarity  
configuration being the opposite polarity of said first polarity configuration so  
that said permanent magnets of said first jaw are oppositely opposed said  
permanent magnets of opposite polarity of said second jaw when said  
magnetizing press is closed;

providing a dielectric brass envelope for fitting between said first and  
second jaws;

placing at least a portion of said magnetizable sheet into said dielectric  
brass envelope, said magnetizable sheet more easily removable from said

24 magnetizing press by said dielectric brass envelope as said dielectric brass  
envelope is not attracted to said magnetizing press and as said dielectric  
26 envelope provides mechanical support for said magnetizable sheet and prevents  
tearing or ripping of said magnetizable sheet when removed from said  
28 magnetizing press;

placing said dielectric brass envelope between said first and second jaws;

30 closing said magnetizing press;

pressing said dielectric envelope and said magnetizable sheet between  
32 said first and second jaws at an elevated pressure, said magnetizable sheet  
magnetized during said pressing to provide a flexible magnetic sheet;

34 heating said magnetizable sheet above a Curie temperature of said  
magnetizable sheet to better magnetize said sheet;

36 cooling said flexible magnetic sheet below said Curie temperature to fix  
said magnetism in said flexible magnetic sheet;

38 removing said flexible magnetic sheet from said magnetizing press  
wherein said flexible magnetic sheet includes permanent magnetic particles  
40 embedded therein with said magnetic particles forming at least one magnetic  
zone of a first polarity and a plurality of magnetic zones of a second polarity;

42 said at least one magnetic zone of first polarity and said plurality of  
magnetic zones of second polarity being positioned contiguous with one another;

44 said at least one magnetic zone of first polarity being contiguous with  
three of said zones of second polarity, said at least one magnetic zone of first  
46 polarity being triangular in shape;

coupling said flexible magnetic sheet to said leather sheet;

48                    providing a sheet of cushioning material, said sheet of cushioning  
material forming a cushioning base;

50                    coupling said sheet of cushioning material to said flexible magnetic sheet  
to provide a three-layer laminated sheet from which flexible magnetic insoles  
52                    may be cut;

                      cutting an insole section from said laminated sheet; and  
54                    providing ventilation holes through said insole section.